



TECHNICAL DATA SHEET FOR  
NIPPON ANTICORROSIVE PAINT

<b>DESCRIPTION</b>	Nippon anticorrosive forms a tough anticorrosive paint film with durability and brushability properties. Recommended for painting on any steel surface for structures on most interior and exterior usage.
<b>TYPE</b>	Air drying long oil alkyd gloss finish
<b>FINISH</b>	Gloss finish
<b>COLOUR</b>	Red, Brown, Black & Grey
<b>FEATURES</b>	Excellent Gloss level Good durability and brushability
<b>APPLICATION DATA</b>	
<b>METHOD</b>	Roller , brush, Spray
<b>THEORETICAL COVERAGE</b>	15 - 16 m <sup>2</sup> /liter at dry film thickness of 40 microns The actual coverage will depend on the surface texture
<b>SURFACE PREPARATION</b>	Eliminate mil – scale, oil, water, dirt, Grease and any foreign matter. Surfaces should be sanded properly before application.
<b>DILUTION</b>	Use Nippolac Mineral Turpentine 10 % max
<b>DRYING TIME</b>	Touch drying    3 -4 Hours at 30 °C ± 2 °C and RH 65 % ± 5% Hard Dry        24 Hours at 30 °C ± 2 °C and RH 65 % ± 5% Over coat       16 Hours at 30 °C ± 2 °C and RH 65 % ± 5%
<b>APPLICATION DETAILS</b>	Stir well before use. Avoid excessive thinning. Provide adequate ventilation.
<b>CLEANING</b>	All equipment should be cleaned with Nippolac Mineral Turpentine immediately after use.



TECHNICAL DATA SHEET FOR  
**NIPPON ANTICORROSIVE PAINT**

**GENERAL INFORMATION**

<b>SOLID CONTENT</b>	65.0 ± 2.% by weight (Based on white colour)
<b>FLASH POINT</b>	34 °C
<b>CONSISTANCY</b>	Ready to use
<b>THINING</b>	Nippolac Mineral Turpentine ( If necessary ) Max 10 %
<b>SPECIFIC GRAVITY</b>	1.35 ± 0.10 (Based on white colour)
<b>PACKING</b>	200 ml, 500 ml, 2 ltr , 1 ltr, 4 ltr, & 200 ltr
<b>SHELF LIFE</b>	Up to 3 years in a tightly sealed container
<b>STORAGE</b>	Store in secure dry conditions inaccessible to children and animals. Containers should be kept tightly closed during storage. Avoid spillage and contamination. Do not empty into drains or water courses.
<b>PRECAUTIONS</b>	Avoid contact with skin and eyes and inhalation of vapours. Use in good natural ventilation and wear protective clothing. Wear suitable respiratory protection when applying. Exclude sources of ignition during application and drying. No smoking.

The information given is intended to give a description of the product performance under specific test conditions. Nevertheless, we cannot assume any responsibility for the use of it since circumstances under which the products are applied in practice are subjected to many variations. We reserve the right to alter the given data without notice

**Enquiries Contacts :**

Nippon Paint Lanka (Pvt) Ltd.  
Nippolac Towers,  
69A, Buthgamuwa Road,  
Rajagiriya,  
Sri Lanka.  
Phone +94-114-600400  
Fax +94-114-600409  
E-mail: info@nipponpaint.com.lk  
Web : www.nipponpaint.lk